

BONDERITE C-IC 1095

Known as Deoxidizer 1095

March 2016

PRODUCT DESCRIPTION

BONDERITE C-IC 1095 provides the following product characteristics:

Technology	Industrial Cleaner
Product Type	Acidic Liquid Cleaner
Application	Metal Pretreatment

BONDERITE C-IC 1095 is an acid product designed for deoxidising and micro-etching of aluminium by dip or spray/cascade applications.

BONDERITE C-IC 1095 is suitable for pre-treatment of aluminium before chromate or non-chromate conversion coating or before chemical or electrochemical polishing.

BONDERITE C-IC 1095 offers the following advantages in comparison with traditional deoxidizers:

- Borate and phosphate free.
- Smooth and even surface due to removal of oxide without affecting the metal surface.
- Energy saving, as the product works at ambient temperature.
- Conversion coatings are more even and adherent.
- Absence of sludge or scales in the treatment tank.
- To work at room temperature produces a lower amount of smokes and vapors guaranteeing higher safety in the working environment.

Application:

BONDERITE C-IC 1095 is used for deoxidising or neutralising, after a suitable cleaning.

In case BONDERITE C-IC 1095 is used as activating cleaning, it is advisable to add a suitable cleaning additive and to carry out the treatment at higher temperatures.

DIRECTIONS FOR USE

Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Operating Parameters:

Average working conditions are the following:

	DIP	SPRAY/CASCADE
Concentration, % v/v	1 to 4	1 to 3
Free acid value	3 to 12	3 to 9
RP	20 max	20 max

Temperature, °C	ambient to 40	ambient to 40
Treatment time, min	3 to 20	1 to 3

Bath Make-up:

- Fill the tank with clean water up to $\frac{3}{4}$ of its volume.
- Activate recirculating pumps and heat the bath to working temperature.
- Add the fixed amount of BONDERITE C-IC 1095 depending on the type of application (spray or dip).
- Bring the solution to the right volume and to the working temperature, let it recirculate for 15 to 20 min.
- Make the final controls.

Bath Control:

The bath is controlled through determination of Free Acid and RP value. A new standard bath at 2% should have a Free Acid value of about 6 mL.

Free Acid:

- Transfer 5 mL of solution into a 250 mL beaker and add 3 to 5 drops of Bromocresol Green Indicator.
- Titrate the sample with 0.1 N Sodium Hydroxide (NaOH) until the colour changes from yellow to blue-green.
- The mL of 0.1 N NaOH used correspond to the Free Acid value.

RP value (reaction products):

- Transfer 5 mL of solution into a 250 mL beaker and add 3 to 5 drops of Phenolphthalein indicator.
- Stir well the sample and titrate with 0.1 N Sodium Hydroxide (NaOH) until the colour changes from colourless to pink.
- Add 1 to 2 g of Sodium Fluoride (NaF).
- In case the pink colour becomes more intense, this means aluminium is present and therefore keep titrate with 0.1 N Hydrochloric Acid (HCl) until the pink colour disappears.
- The ml of 0.1 N HCl used correspond to the RP value of the bath.

Bath Replenishment:

The bath is replenished according to the Free Acid value of the solution.

Add 3.3 kg (3 litres) of BONDERITE C-IC 1095 for each missing point and for each 1,000 L of bath.

The bath of BONDERITE C-IC 1095 can be easily monitored with automatic devices.

The age level of the bath is monitored by determination of RP value that must be maintained under 20 mL.

Technical Service will suggest the appropriate actions for the bath managing according to the specific application.

Particular Advices:

In case of oil formation on the surface, it is recommended to carry out a partial overflow of the solution in order to keep it free from contamination.

Tanks and all parts of the plant in contact with the concentrated product must be made or coated with anti-acid material (PVC or polythene are recommended).

The part of the plant in contact with the product in solution (tanks, conveyors, etc.) can be made of stainless steel 316L. Slight differences in the product appearance do not affect its efficiency and performances.

Classification:

Please refer to the corresponding **Material Safety Data**

Sheets for details on:

Hazards identification

Transport information

Regulatory information

Storage:

Recommended Storage Temperature, °C 0 to 35

Shelf life, months 24

(in unopened original packaging)

ADDITIONAL INFORMATION**Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0